

---

# Product Bulletin

Reference PS-Sec

March 1997

FastFact # 5515

## Gerber Security Label Stock

### DESCRIPTION

Gerber Security films are 2 mil, dimensionally stable, polyester-based films that resist tearing and abrasion. They have been formulated for use with Gerber Digital Color Printing Systems and GerberColor™ foils. They are coated with a tamper-evident adhesive system and are backed with a 90# lay-flat liner.

Gerber Security Label Stock is available in chrome silver.

### INTENDED APPLICATIONS

Gerber Security Films are ideally suited for a wide variety of commercial and industrial label applications in which tamper resistance, heat resistance and dimensional stability are required.

When labels printed on Gerber Security Label Stock are adhered to substrates such as stainless steel, acrylic, or polypropylene, a "VOID" pattern will be left behind when the material is removed. The removed label can not be reapplied. The user should determine the suitability of all substrates prior to actual application.

Activation of the tamper-evident feature will occur approximately two hours after application at 60°F to 75°F (16°C to 24°C). This feature will become permanently non-functional when continuously exposed to temperatures above 104° F (40° C).

Due to the mirror-like finish of the chrome silver, it is not suitable for the scanning of bar code information.

Only solid fills should be printed on this material. The minimum recommended stroke width is .009" (.23mm).

These films are not intended for backlit applications or applications where petrochemical exposure may occur. If petrochemical exposure is anticipated, refer to the section below on protecting graphics.

### APPLICATION TECHNIQUES

Dry application methods should be used with Gerber Security Label Stock and panels should be butted.

Gerber standard tack application tape is required for all graphics produced with Gerber Digital Color Printing Systems.

### SUBSTRATE PREPARATION

Before applying your graphic, wash the surface of your substrate with warm water and detergent. Do not use soaps or other cleaners with lotions or creams as they will leave a residue. Thoroughly rinse the surface and allow it to completely dry.

Saturate a clean paper towel with a solvent-based cleaner and wipe the substrate surface. Be certain to follow all manufacturer safety guidelines when using any solvent. Dry the surface with a lint-free paper towel before the solvent evaporates.

---

If applying to glass, solvent wipe the surface with a 2 to 1 mixture of water and isopropyl alcohol. Glass temperatures can vary across the surface. These temperature variations can produce stresses which may cause the glass to break. Use caution when applying to glass.

Some polycarbonate substrates may weaken when certain vinyl films are applied to them. Because of this possibility, the user will need to determine if safety items such as helmets, safety shields, and some windshields are compatible with their vinyl's adhesive.

Many paint systems (e.g. two-part urethane) and some polycarbonate substrates will outgas if they are not fully cured. Outgassing can cause permanent bubbling in most films; substrates should be tested for outgassing prior to final application.

## **PERFORMANCE LIFE (UNPRINTED)**

Gerber Security Labels have two-year exterior durability when applied vertically.

Performance statements are based upon field experience and exposure tests conducted throughout the United States. Substrate selection, exposure angle, environmental conditions, and maintenance of markings will affect actual performance. Continuous exposure in regions that experience maximum sunny days will result in decreased performance. Extreme temperature cycling over a short time may result in film cracking. This product is not recommended for horizontal applications.

## **PRINTING**

If your software material selection palette does not have Gerber Security Label Stock, use Scotchcal™ 220 normal print settings.

GerberColor Spot (GCS) Series, GerberColor Process (GCP) SUPER CMYK™ Series, GerberColor Medal (GCM) Series and GerberColor Transparent (GCT) Series Foils can be used to print onto Security Label Stock.

## **CUTTING**

Gerber Security Films can be cut on any 15" GRAPHIX ADVANTAGE® compatible plotter. A 30° SuperSharp blade is recommended. Plotters can be set to full speed.

The user should perform a test cut to determine the ideal tool force setting.

## **PROTECTING GRAPHICS**

Gerber Scientific Products, Inc. offers two products that are designed to protect vinyl and printed graphics.

Gerber Guard™ is a durable, dimensionally stable, glossy vinyl overlamine. This film has a petrochemical-resistant construction and is intended to be used when markings may be exposed to petrochemical spillage and/or severe handling conditions.

Abrasion Guard™ is a clear, top-coat GerberColor Foil designed to protect graphics from moderate contact or handling.

## **SHELF LIFE AND STORAGE**

Apply film within one year of receipt. Printed graphics should also be applied within one year. Film and printed graphics (with or without premask) should be kept in a clean area free from excessive moisture and direct sunlight. Maintain temperature at 70° F (21°C) and humidity at 50%.

Use a paper interleaf between layers of stacked or rolled printed materials. Do not stack printed graphics face to face.

---

## MAINTENANCE

To clean printed graphics, use a mild, non-abrasive soap with a soft cloth or sponge. Avoid using alcohol-based cleansers or soaps containing grit or abrasives

## PHYSICAL PROPERTIES

Thickness	2.4 – 2.5 mil with adhesive
Film Color	Chrome silver
Adhesive	Pressure sensitive
Adhesive Color	Clear
Liner	90# lay flat
Tensile Strength	N/A
Elongation	0
Dimensional Stability	No measurable shrinkage
Application Temp	32°F to 100°F (0°C to 38°C)
Removal Temp	N/A
Operating Temp	-40°F to 104°F (-40°C to +40°C)

## CHEMICAL RESISTANCE (UNPRINTED)

Chemical Agent	Result
Household Cleaners	No effect
Mild acids	No effect
Motor oil	No effect
Water	No effect

## RELATED LITERATURE

GerberColor Spot (GCS) Series, GerberColor Process (GCP) SUPER CMYK Series, GerberColor Medal (GCM) Series, GerberColor Transparent (GCT) Series, Gerber Guard, and Abrasion Guard (GerberColor Finishing GCF) Product Bulletins.

For help with questions concerning Gerber products, please call your distributor or Gerber Customer Service at 1-800-222-7446 or (860)643-1515.

---

GerberColor, GerberColor SUPER CMYK, Gerber Guard, and Abrasion Guard are Trademarks of Gerber Scientific Products, Inc. 3M and Scotchcal are Trademarks of The 3M Corporation.